

**SCHEDA TECNICO-COMMERCIALE**  
**Commercial - Technical Data**

Xinshengda Internal Quality Standard Requirements, Version 2025-A

**Basic test information**

|                    |               |                     |              |                                                                                     |
|--------------------|---------------|---------------------|--------------|-------------------------------------------------------------------------------------|
| Sample Information | Card No.:     | 202609243067002     | Sample Photo |  |
|                    | Material:     | A3067               |              |                                                                                     |
|                    | Color:        | Chestnut Brown      |              |                                                                                     |
| Type of Test       | Internal Test | Sample Receipt Date | 2026.9.23    | Report Issue Date 2026.9.24                                                         |

| Test Item                        | Test Method      | Specification Requirement | Test Result                                      | Assessment |
|----------------------------------|------------------|---------------------------|--------------------------------------------------|------------|
| Fibre Content                    | ISO 1833-20:2018 | /                         | 77.8% Nylon                                      | Pass       |
|                                  |                  |                           | 22.2% Spandex                                    |            |
| Color Fastness to Rubbing        | ISO 105-X12:2016 | Dry ≥ 4                   | Dry: 4-5                                         | Pass       |
|                                  |                  | Wet ≥ 3-4                 | Wet: 4-5                                         |            |
| Pilling Resistance               | ISO 12945-2:2020 | ≥ 3-4                     | 4-5                                              | Pass       |
| Dimensional Change After Washing | ISO 3759:2011    | (-3.0% ~ +1.0%)           | Wale direction: -2.0%<br>Course direction: -0.5% | Pass       |
|                                  | ISO 6330:2021 4N | (+) indicates extension   |                                                  |            |
|                                  | ISO 5077:2007    | (-) indicates shrinkage   |                                                  |            |
| Formaldehyde Content             | ISO 14184-1:2011 | Not Detected              | Not Detected                                     | Pass       |
| pH Value                         | ISO 3071:2020    | 4.0-7.5                   | 6.6                                              | Pass       |

Certifications



Note / Notes:

We recommend testing each dyebath before any treatment or application other than cutting and sewing.

To improve our products, we reserve the right to modify these, as and when necessary.